

HLP9947

Technical Data Sheet

HDPE

Pipe Extrusion

Applications

- Pressure Pipe
- Municipal Pipe
- Mining Pipe
- PPI Designations PE4710

Properties

- Phillips Process®
- Excellent Resistance to Slump
- Good Resistance to Slow Crack
- Growth Good Long-Term Hoop Strength

PROPERTIES

VALUE

METHOD

PROPERTIES	VALUE	METHOD
High Load Melt Index (gm/10 min)	9.0	ASTM D1238
Density (gm/cc)	0.947	ASTM D1505
Tensile at Yield (psi)	> 3500	ASTM D638
Elongation at Break (%)	> 700	ASTM D638
Flexural Modulus (psi)	120500	ASTM D790
PENT Slow Crack Growth (hours)	> 500	ASTM D1473
Hydrostatic Design Basis, 23°C (psi)	1600	ASTM D2837
Hydrostatic Design Basis, 60°C (psi)	1000	ASTM D2387

Additional Certifications

This material may comply with additional regulations not included on this technical data sheet. Please contact your Trademark representative for details.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.