

LD2920 Series

Technical Data Sheet

LDPE Film Resin

Applications

- General Purpose Liner Applications
- Trash Bags
- Industrial Packaging

Properties

- Excellent Processability
- Excellent Drawdown
- Good Toughness

Grades

- 2920B - No additives
- 2920F - Medium slip & Antiblock

PROPERTIES

VALUE

METHOD

PROPERTIES	VALUE	METHOD
Melt Index, MI ₂ (gm/10 min)	2.0	ASTM D1238
Density (gm/cc)	0.920	ASTM D1505
Haze* (%)	11.0	ASTM D1003
Specular Gloss @ 45°	-	ASTM D2457
Dart Impact	110	ASTM D1709
Ultimate Tensile MD/TD (psi)	3100/2300	ASTM D882
Elongation MD/TD (%)	200/510	ASTM D882
1% SEcant Modulus MD/TD (psi)	26000/31500	ASTM D882
Elmendorf Tear Strength MD/TD (g)	320/110	ASTM D1922

Typical film property as measured on a 2.0 mil blown film sample fabricated at a 2.5:1 B.U.R.

*Base polymer only.

FDA

This material complies with FDA regulations in 21 CFR, section 177.1520, paragraph C, section 2.1, for use in articles that contact non-alcoholic food.

Processing

Extrusion melt temperatures of 360° to 390° are recommended for Trademark's LD2920 Series with blow-up ratios of 1.5:1 or higher.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.