

LLB1918 Series

Technical Data Sheet

LLDPE Film Resin

Applications

- Heavy Duty Sacks
- Liners
- Food Packaging
- Commercial Packaging

Properties

- Butene Comonomer
- Excellent Puncture
- Excellent Drawdown
- Excellent Heat Seal

Grades

- LLB1918B - Barefoot
- LLB1918C - No Slip & High Antiblock
- LLB1918F - High Slip & Antiblock

PROPERTIES	VALUE	METHOD
Melt Index, MI ₂ (gm/10min)	1.0	ASTM D1238
Density (gm/cc)	0.918	ASTM D1505
Haze* (%)	17	ASTM D1003
Specular Gloss @ 45°	45	ASTM D2457
Dart Impact (gms/mil)	110	ASTM D1709
Elmendorf Tear MD/TD (g/mil)	130/320	ASTM D1922
Tensile at Break MD/TD (psi)	6600/4600	ASTM D882
Elongation at Break MD/TD (%)	570/730	ASTM D882
1% Secant Modulus MD/TD (psi)	27000/27500	ASTM D882

Typical film property as measured on a 1.0 mil blown film sample fabricated at a 2.5:1 B.U.R.

*Base polymer only.

FDA

This material complies with FDA regulations in 21 CFR, section 177.1520, paragraph C, section 3.1(a).

Processing

Extrusion melt temperatures of 400° to 450°F are recommended for Trademark's LLB1918 Series with blow-up ratios of 1.5:1 or higher.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.