

## HH180

Technical Data Sheet

## High Heat Crystal Extrusion & Foam

### Applications

- Foam Disposables
- Medical
- Oriented Polystyrene Sheet
- Packaging

### Properties

- High Heat Resistance
- High Tensile Strength
- High Stiffness

PROPERTIES	VALUE	METHOD
Melt Flow (gm/10 min)	1.8	ASTM D1238
Specific Gravity (gm/cc)	1.04	ASTM D792
Tensile Strength@Y <sup>(2)</sup> , 2 in/min (psi)	7700	ASTM D638
Tensile Modulus <sup>(2)</sup> , 2 in/min (psi)	423000	ASTM D638
Tensile Elongation <sup>(2)</sup> , 2 in/min (%)	2.0	ASTM D638
Flexural Strength, 0.1 in/min (psi)	15000	ASTM D790B
Flexural Modulus, 0.1 in/min (psi)	456000	ASTM D790B
Notched Izod at 73°F, (ft-lb/in)	0.4	ASTM D256
Vicat Softening Temp.	226	ASTM D1525
Deflection Temp. Under Load <sup>(1)</sup> (F°)	183	ASTM D648
Mold Shrinkage, 24 hours (in / in)	0.003-0.007	ASTM D955
Thermal Expansion, (4x10 <sup>-5</sup> , in/in/°F)	5.0	ASTM D696
Light Transmission (%)	90	ASTM D1003
Haze (%)	1.0	ASTM D1003
Refractive Index (sodium D line)	1.59	ASTM D542

### FDA

This material complies with FDA regulations in 21 CFR, section 177.1640.

### Notes

- (1) DTUL tested under 264 psi.
- (2) Thickness of samples tested, 0.125 inch.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.