

## mLLD1916 Series

## LLDPE Film Resin

### Technical Data Sheet

#### Applications

- Heavy Duty Packaging
- High Strength Clarity Packaging
- Seal Layer in Coextrusions
- Enhancing Monolayer Films

#### Properties

- Metallocene Catalyst
- Excellent Haze and Gloss
- Excellent Strength
- Excellent Heat Seal

#### Grades

- 1916B - Process Aid (PA)
- 1916F - PA, High Slip & Antiblock

#### PROPERTIES

#### VALUE

#### METHOD

PROPERTIES	VALUE	METHOD
Melt Index, MI <sub>2</sub> (gm/10min)	1.4	ASTM D1238
Density (gm/cc)	0.916	ASTM D1505
Haze* (%)	4.0	ASTM D1003
Specular Gloss @ 45°	135	ASTM D2457
Dart Impact (gms/mil)	1100	ASTM D1709
Elmendorf Tear MD/TD (g/mil)	230/500	ASTM D1922
Tensile at Yield MD/TD (psi)	1970/1500	ASTM D882
Tensile at Break MD/TD (psi)	7550/7390	ASTM D882
Elongation of Break MD/TD (%)	470/580	ASTM D882
1% Secant Modulus MD/TD (psi)	24000/26300	ASTM D882
Film Puncture Force (lbf)	18.6	ASTM D3763
Seal Initiation Temperature (°F)	199	ASTM D3763

Typical 1m property as measured on a 1.0 mil blown 1m sample fabricated at a 2.5:1 B.U.R.

\*Base polymer only.

#### FDA

This material complies with FDA regulations in 21 CFR, section 177.1520, paragraph C, section 2.1, for use in articles that contact non-alcoholic food.

#### Processing

Extrusion melt temperatures of 360° to 400°F are recommended for Trademark's mLLD1916 Series with blow-up ratios of 1.5:1 or higher.

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability, or completeness of such information for its particular use. There is no warranty against patent infringement, and Trademark Plastics Corporation shall not be liable for any loss, damage, or injury that may occur from use of this information. No statement herein shall be construed as an endorsement of any product or process.

For more information about our products, please contact your local sales representative or call 908.925.5900.